

Batbets Interstain

Varnishes

Wood Stain



PRODUCT DESCRIPTION

A mahogany wood stain for staining brightwork and restoring colour to faded timber.

- * Penetrating formulation
- * Resistant to fade for interior and exterior use
- * Can be mixed with one-pack varnishes (as per thinning recommendation) to achieve a darker finish

PRODUCT INFORMATION

Colour	YAA825-Mahogany
Finish	Low sheen
Specific Gravity	0.94
Volume Solids	1%
Typical Shelf Life	2 yrs
VOC (As Supplied)	932 g/lt
Unit Size	375 ml

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	3 hrs		2 hrs		1 hrs		30 mins	
	Overcoating							
	Substrate Temperature							
Overcoated By	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Batbets Interstain	4 hrs	-	3 hrs	-	2 hrs	-	1 hrs	-
Goldspar	4 hrs	-	3 hrs	-	2 hrs	-	1 hrs	-
Goldspar Satin	4 hrs	-	3 hrs	-	2 hrs	-	1 hrs	-
Original	4 hrs	-	3 hrs	-	2 hrs	-	1 hrs	-
Schooner	4 hrs	-	3 hrs	-	2 hrs	-	1 hrs	-

Note: For all two-pack products, including Epiglass HT9000, allow 2-3 days before overcoating.

APPLICATION AND USE

Preparation	Sand with 80-180 grade (grit) paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying the first coat.
Method	Apply one or more coats as required for colour. Finish with International Varnishes. Alternatively, mix with International Varnish as per thinning recommendation to achieve a darker finish.
Hints	Mixing Stir or shake thoroughly. Thinner YTA800 Thinners No.1 Cleaner YTA800 Thinners No.1
Some Important Points	Product temperature should be minimum 10°C and maximum 35°C. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all types of wood. Only use on bare wood. Can be mixed with all International varnishes to give a darker tint.
Number of Coats	1-3 as required
Application Methods	Brush. Also cloth and pad

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Batbets Interstain to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: Batbets Interstain should be kept in securely closed containers during transport and storage.
----------------	--

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2015.

Batbets Interstain

Varnishes

Wood Stain



Safety

GENERAL:

Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL:

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Batbets Interstain cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.