

Interdeck

Finishes

Slip Resistant Deck Paint



PRODUCT DESCRIPTION

Interdeck provides an excellent slip resistant finish. It contains a fine aggregate and will apply easily on all substrates.

* Low sheen finish prevents dazzling reflected sunlight off decks

* Easy application

The tough polyurethane resin protects decks against everyday wear and tear.

PRODUCT INFORMATION

Colour	YJB000-White, YJB923-Squall Blue, YJC089-Cream, YJF684-Grey
Finish	Semi Gloss
Specific Gravity	1.4
Volume Solids	56%
Typical Shelf Life	2 yrs
VOC (As Supplied)	357 g/lit
Unit Size	500 ml (White only), 1 lt, 4 lt (White only)

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Dry To Walk On	4 days		3 days		2 days		1 days	
Touch Dry	5 hrs		4 hrs		3 hrs		2 hrs	

	Overcoating							
	Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Overcoated By								
Interdeck	24 hrs	4 days	20 hrs	3 days	16 hrs	2 days	12 hrs	1 days

APPLICATION AND USE

Preparation

PREVIOUSLY PAINTED SURFACES

In Good Condition: Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper. Apply one coat of One UP all over followed by 1-2 coats of Interdeck. In Poor Condition Remove all previous coatings and prime the substrate.

TIMBER: Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying primer. Prime with One UP.

STEEL: Degrease with solvent. Gritblast to Sa 2½ - near white metal surface. If gritblasting is not possible, grind the metal surface with 24-36 grit abrasive discs to a uniform, clean, bright metal surface with a 50-75 microns anchor pattern. Use angle grinder on small areas. Clean thoroughly and allow to dry. Prime with One UP or Interprotect.

ALUMINIUM: Degrease with solvent or suitable detergent cleaner. Sand well using 24-120 grade (aluminium compatible) paper. Coarser grades are recommended to achieve optimum adhesion. Clean thoroughly and allow to dry. Prime with One UP or Interprotect as soon as possible (within 4 hours).

GRP: In new or excellent condition Degrease with solvent or suitable detergent cleaner. Sand well using 180-220 grade paper. Clean thoroughly and allow to dry. No primer required - apply One UP direct to GRP.

AGED/WEATHERED GELCOATS: Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with the appropriate undercoat/primer depending on the application method prior to topcoat application. Please speak to your local sales representative for more information.

ALL SUBSTRATES: Use One UP.

Method

Sand the undercoat with 180-220 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.

Hints

Mixing: Stir well before use.

Thinner: YTA800 International Enamel Thinner No 1.

Thinning: Thinning is not recommended.

Cleaner: YTA800 International Enamel Thinner No 1.

Ventilation and Humidity Control: Apply in dry, well ventilated conditions.

Other: For best results either stipple by brush or use a mohair roller.

Please refer to your local representative or visit www.international-yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2023.

Interdeck

Finishes

Slip Resistant Deck Paint



Some Important Points	Product temperature should be minimum 10°C and maximum 30°C. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all substrates and filled surfaces. Not suitable for permanently immersed surfaces. Do not clean with highly alkaline cleaners.
Number of Coats	1-2
Coverage	(Theoretical) - 11.2 m ² /L (Practical) - 10.08 m ² /L
Recommended DFT per coat	50 microns dry
Recommended WFT per coat	93 microns wet
Application Methods	Brush, Roller. Not suitable for spray application.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	TRANSPORTATION: Interdeck should be kept in securely closed containers during transport and storage. STORAGE: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interdeck to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.
Safety	DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. Always use gloves and goggles and keep skin protected with overalls. Users should ensure they have a copy of the Material Safety Datasheet for this product and that they are familiar with all the safety directions before use.
IMPORTANT NOTES	<i>The technical information and suggestions for use and application presented herein are not intended to be exhaustive, but they represent the best information available to use and are believed to be reliable. They should not, however, be construed as controlling suggestions and there is no warranty of performance of our materials either expressed or implied. We urge that users of our materials conduct confirmatory tests to determine final suitability for their specific end uses. Because this datasheet is subject to changes from time to time, it is the user's responsibility to check that this sheet is current prior to using the product.</i>

Please refer to your local representative or visit www.international-yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2023.