

PRODUCT DESCRIPTION

Interdeck provides an excellent slip resistant finish. It contains a fine aggregate and will apply easily on all substrates.

* Low sheen finish prevents dazzling reflected sunlight off decks

* Easy application

* Available in a range of colours

The tough polyurethane resin protects decks against everyday wear and tear.

PRODUCT INFORMATION

Color	YJB000-White, YJC089-Cream, YJF684-Gray, YJG009-Sand Beige
Finish	Low sheen
Specific Gravity	1.4
Volume Solids	56%
Typical Shelf Life	2 yrs
VOC (As Supplied)	330 g/lit
Unit Size	1 US Quart

DRYING/OVERCOATING INFORMATION

	Drying							
	41°F (5°C)		59°F (15°C)		73°F (23°C)		95°F (35°C)	
Touch Dry [ISO]	5 hrs		4 hrs		3 hrs		2 hrs	
Dry To Walk On	4 days		3 days		2 days		1 days	

	Overcoating							
	Substrate Temperature							
	41°F (5°C)		59°F (15°C)		73°F (23°C)		95°F (35°C)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interdeck	24 hrs	4 days	20 hrs	3 days	16 hrs	2 days	12 hrs	1 days

APPLICATION AND USE

Preparation	<p>FIBERGLASS (GELCOAT): In Good Condition: Begin by scrubbing well using soap and water and a stiff brush. Rinse with fresh water and allow to dry. Wipe a small area with a clean rag that has been wetted with Fiberglass Solvent Wash 202. While the surface is still wet, wipe with a clean, dry rag. Continue this process until the entire surface has been cleaned. Sand using 180-220 grade (grit) paper. Remove sanding residue. MOLDED IN NON-SKID SURFACES: Scrub with Fiberglass Surface Prep YMA601 or Solvent Wash 202V using a 3M Doodlebug™ and a maroon Scotch-Brite® pad. Rinse with fresh water. PREVIOUSLY PAINTED SURFACES: In Good Condition: The surface must be clean and dry. Sand with 220-320 grade (grit) paper. Remove sanding residue. In Poor Condition: Remove all previous coatings and prime the substrate. BARE WOOD: Sand surface, wipe clean. Apply Pre-Kote Plus. Sand surface, wipe clean. METAL: Use Pre-Kote Plus or Interprotect 2000E to prime the surface of the prepared metal. See the Interprotect 2000E Technical Datasheet for bare metal preparation guidelines. FIBERGLASS/CLEAR EPOXY: Clean as for Fiberglass (Gelcoat) above. Sand with 80 grade (grit) paper. Remove sanding residue. Apply one coat of Epoxy Barrier-Kote 404/414.</p>
Method	Sand the primer with 180-220 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.
Hints	<p>Mixing Stir well before use. Thinner Brushing Liquid 333 Cleaner Special Thinner 216. Ventilation and Humidity Control Apply in dry, well ventilated conditions. Other For best results either stipple by brush or use a mohair roller.</p>
Some Important Points	Product temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all substrates and filled surfaces. Not suitable for permanently immersed surfaces. Do not clean with highly alkaline cleaners.

Please refer to your local representative or visit www.interlux.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.

Interdeck

Finishes

Slip Resistant Deck Paint



Number of Coats	1-2
Coverage	(Theoretical) - 11.2 m ² /L (Practical) - 10.08 m ² /L
Recommended DFT per coat	2 mils dry
Recommended WFT per coat	3.6 mils wet
Application Methods	Brush, Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interdeck to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Interdeck should be kept in securely closed containers during transport and storage.

Safety

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Interdeck cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit www.interlux.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.