

PRODUCT DESCRIPTION

Interdeck provides an excellent slip resistant finish. It contains a fine aggregate and will apply easily on all substrates.

* Low sheen finish prevents dazzling reflected sunlight off decks

* Easy application

* Available in a range of colours

The tough polyurethane resin protects decks against everyday wear and tear.

PRODUCT INFORMATION

Colour	YJB000-White, YJB923-Squall Blue, YJC089-Cream, YJF684-Grey, YJG009-Sand Beige Not all colours or pack sizes are available in all countries.
Finish	Semi Gloss
Specific Gravity	1.4
Volume Solids	56%
Typical Shelf Life	2 yrs
VOC (As Supplied)	330 g/lt
Unit Size	750 ml

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	5 hrs		4 hrs		3 hrs		2 hrs	
Dry To Walk On	4 days		3 days		2 days		24 hrs	

	Overcoating							
	Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interdeck	24 hrs	4 days	20 hrs	3 days	16 hrs	2 days	12 hrs	1 days

APPLICATION AND USE

Preparation

PREVIOUSLY PAINTED SURFACES

In Good Condition Wash down with Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

In Poor Condition Remove all previous coatings and prime the substrate.

PRIMING All preparation for bare substrates is covered on the appropriate primer datasheet.

BARE WOOD Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying products recommended for application direct to wood (see specific coating systems).

STEEL Degrease with solvent, Super Cleaner or a suitable liquid detergent. Gritblast to Sa 2½ - near white metal surface. If gritblasting is not possible, grind the metal surface with 24-36 grit abrasive discs to a uniform, clean, bright metal surface with a 50-75 microns anchor pattern. Use angle grinder on small areas. Clean thoroughly and allow to dry. Pre-prime using an International primer as detailed for specific coating systems.

ALUMINIUM Degrease with solvent, Super Cleaner or a suitable liquid detergent. Sand well using 24-120 grade (aluminium compatible) paper. Coarser grades are recommended to achieve optimum adhesion. Clean thoroughly and allow to dry. Pre-prime using an International primer as soon as possible (within 8 hours) as detailed for specific coating systems.

GRP Degrease with solvent, Super Cleaner or a suitable liquid detergent. Sand well using 60-120 grade paper. Clean thoroughly and allow to dry. Pre-prime using an International primer as detailed for specific coating systems.

AGED/WEATHERED GELCOATS Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with the appropriate undercoat/primer depending on the application method prior to topcoat application. Please speak to your local sales representative for more information.

ALL SUBSTRATES If any filling is required use the appropriate product from the International range .

Method

Sand the primer with 180-220 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.

Please refer to your local representative or visit www.international-yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2024.

Interdeck

Finishes

Slip Resistant Deck Paint



Hints	Mixing Stir well before use. Thinner YTA800 Thinner No.1 Cleaner Thinner No.1 Ventilation and Humidity Control Apply in dry, well ventilated conditions. Other For best results either stipple by brush or use a mohair roller.
Some Important Points	Formulated for exterior use. Product temperature should be minimum 10°C/50°F and maximum 30°C/86°F. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all substrates and filled surfaces. Not suitable for permanently immersed surfaces. Do not clean with highly alkaline cleaners.
Number of Coats	1-2
Coverage	(Theoretical) - 11.2 m ² /L (Practical) - 10.08 m ² /L
Recommended DFT per coat	50 microns dry
Recommended WFT per coat	89 microns wet
Application Methods	Brush, Roller. Not suitable for spray application.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interdeck to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: Interdeck should be kept in securely closed containers during transport and storage.
Safety	GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Interdeck cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.
IMPORTANT NOTES	<i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i>

Please refer to your local representative or visit www.international-yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2024.