

Toplac Plus

Finishes

Premium High Durability Yacht Gloss Enamel



PRODUCT DESCRIPTION

Toplac Plus is a silicone alkyd premium gloss yacht enamel for all substrates above the waterline. It is easy to apply by roller without the need for tipping. Toplac Plus contains UV filters for increased durability.

* Range of bright colors.

* Unique chemical structure for superior definition and durability.

* Excellent flow characteristics

PRODUCT INFORMATION

Color	YLK000-Snow White, YLK027-Cream, YLK101-Yellow, YLK151-Platinum, YLK184-Mediterranean White, YLK187-Ivory, YLK299-Rochelle Red, YLK541-Donegal Green, YLK684-Atlantic Gray, YLK936-Lauderdale Blue, YLK933-Oxford Blue, YLK999-Jet Black, YLK194-Oyster White, YLK198-Matthorn White, YLK292-Bounty, YLK192-Off White, YLK501-Rustic Red, YLK830-Sapphire Blue, YLK990-Flag Blue, YLK315-Anthracite Gray, YLK237-Sundown Buff, YLK256-Sea Foam Green, YLK898-Bondi Blue, YLK962-Boston Whaler Blue, YLK904-Ice Blue
Finish	High Gloss
Specific Gravity	1.1
Volume Solids	51%
Typical Shelf Life	2 yrs
VOC (As Supplied)	404 g/lit
VOC (EU Solvent)	367 g/kg EU Solvent Emissions Directive (Council Directive 1999/13/EC)
Unit Size	1 US Quart, 1 US Gallon Not all colors are available in all sizes.

DRYING/OVERCOATING INFORMATION

	Drying							
	41°F (5°C)		59°F (15°C)		77°F (25°C)		95°F (35°C)	
Touch Dry [ISO]	6 hrs		3 hrs		2 hrs		60 mins	

	Overcoating							
	Substrate Temperature							
Overcoated By	41°F (5°C)		59°F (15°C)		77°F (25°C)		95°F (35°C)	
	Min	Max	Min	Max	Min	Max	Min	Max
Toplac Plus	24 hrs	4 days	16 hrs	3 days	8 hrs	2 days	6 hrs	24 hrs

APPLICATION AND USE

Preparation	<p>PREVIOUSLY PAINTED SURFACE:</p> <p>In Good Condition: Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper. Remove sanding residue. Wipe with Brushing Liquid 333 and allow to dry completely.</p> <p>In Poor Condition: Remove all previous coatings and prime the substrate.</p> <p>PRIMING: Please refer to the primer or primer/undercoat technical datasheet.</p> <p>ALL SUBSTRATES: Prime with a suitable primer or primer/undercoat (Pre-Kote Plus/Epoxy Primekote).</p>
Method	Sand the undercoat smooth with 320-400 grade (grit) wet or dry paper. Remove dust with a dust wipe. Apply 2-3 coats of Toplac Plus.
Hints	<p>Mixing: Stir well before use.</p> <p>Thinner: Reducing Solvent (Y2333N) - Brush or Special Thinner 216 (Y216) - Spray.</p> <p>Thinning: Add 10% Reducing Solvent-Brush (Y2333N) to ease the application by brush/roller. The thinner quantity can be adjusted with climate conditions. At temperature above 75°F (25°C) an extra 5% Reducing Solvent (Y2333N) should be added.</p> <p>Cleaner: Brushing Liquid 333, Reducing Solvent (Y2333N) - Brush or Special Thinner 216 (Y216) - Spray.</p> <p>Ventilation and Humidity Control: Apply in dry, well ventilated conditions.</p>
Some Important Points	<p>Toplac Plus may discolor if used at temperatures above 80°C/176°F. Not suitable for permanently immersed surfaces. Do not use below 5°C/41°F.</p> <p>Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F.</p> <p>Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.</p> <p>Product temperature should be minimum 15°C/59°F and maximum 35°C/95°F.</p>

Please refer to your local representative or visit www.interlux.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.

Toplac Plus

Finishes

Premium High Durability Yacht Gloss Enamel



	Avoid applying late in the evening as condensation can cause a loss of gloss during overnight cure.
Compatibility/Substrates	Use over suitably prepared and undercoated surfaces or existing paint schemes.
Number of Coats	Apply 2-3 coats. Only 1 coat may be required for touch-up/repair.
Coverage	(Theoretical) - 652 ft ² /gal per coat. (Practical) - 587 ft ² /gal per coat.
Recommended DFT per coat	1-1.5 mils dry
Recommended WFT per coat	2-3 mils wet
Application Methods	Brush, Roller, Spray. The application by roller does not need tipping.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Toplac Plus to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.
Safety	TRANSPORTATION: This product should be kept in securely closed containers during transport and storage. GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Reminders of Intergrip cannot be disposed of through the municipal waste route or dumped without permit.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit www.interlux.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.